

Textile Processing Compound

Let You LEAD The Process

E-mail : contact@nestorindustries.com

Softner - EL

Micro amino silicone

Provides excellent surface smoothness with bounciness

Features

- ✓ Imparts excellent surface softness to fabrics.
- ✓ Improves sew ability.
- ✓ Along with synthetic resin finishes improves the properties of goods
- ✓ Does not affect the brightness of dyed shades.
- ✓ Produces finish effects that are fast to washing and dry cleaning.

Type	Non ionic
Constitution	Reactive polydimethyl siloxane.
Appearance	Clear Solution
pH	5.5 – 6.5
Solubility	Readily soluble in water.
Storage	Stable under normal conditions.

Application

(1) Padding on all types of fibres ;

Softner - EL - 20 to 40 gpl

pH— 5

Pad : 65 – 85 % pick up

Pad-dry-cure at 170 Deg.C.

(2) Exhaust method ;

Softner - EL - 1 to 2 % O. W. F.

at pH 4.5 – 5.5

for 25 -30 mins. At 30 – 40 Deg. C

The product appearance varies from batch to batch. The colour & viscosity may vary from batch to batch and its intensity is not an indication of product strength.

NONWARRANTY: The suggestions and data in this bulletin are based on information we believe to be reliable. They are offered in good faith but without guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions on an experimental basis before adopting them on a commercial scale.

Head Office Address: Plot No – 538, GIDC, Pandesara, Surat – 394221

Contact No. - +91 8306083020, +91 9377781836 || Website : www.nestorindustries.com