

TECHNICAL BULLETIN

Textile Processing Compound



Let You LEAD The Process

E-mail : contact@nestorindustries.com

Nestogen JDP

A versatile Anionic
Wetting agent cum
detergent

'Nestogen JDP' is high performance wetting agent cum detergent designed for processes where exceptionally high wetting is required like open width continuous bleaching.

Features

- High Efficiency in Emulsification of oils and waxes
 - Good detergency for cotton and also for rayon and other synthetic-fiber textiles
 - Effective wetting properties
 - Excellent rinsability
 - Good dispersing properties
 - Outstanding stability to alkali and caustic
 - Synergism with sequesterants in the control of iron and other metal ions.
 - Low toxicity
 - Rust inhibition
-

Type	Non-ionic
Constitution	Free acid of complex organic ethoxylate
Appearance	Clear liquid
Solubility	Easily soluble in cold water.
Compatibility	Stable to alkalies, acids, electrolytes, hard water and compatible with auxiliaries used in bleach bath.
Storage	Stable under normal conditions.
Application	<p>In the continuous processing the dwell time of fabric in the bath is very short and hence high wetting to ensure uniform and fast pick up of bath liquor.</p> <p>'Nestogen JDP' a specially designed wetting agent which ensures fast wetting of the fabric in continuous preparation and yield good absorbency and whiteness.</p>

The product appearance varies from batch to batch. The colour & viscosity may vary from batch to batch and its intensity is not an indication of product strength.

NONWARRANTY: The suggestions and data in this bulletin are based on information we believe to be reliable. They are offered in good faith but without guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions on an experimental basis before adopting them on a commercial scale.

Head Office Address: Plot No – 538, GIDC, Pandesara, Surat – 394221
Contact No. - +91 8306083020, +91 9377781836 || Website : www.nestorindustries.com

1. CONTINUOUS PROCESS**1.1 Pad-steam (Roller-bed steamer, J-Box and U-Box)**

	Desize	Scouring	Bleaching
Nestogen JDP	2 g/l	2-4 g/l	3-4 g/l
Hydrogen Peroxide (50%)	3-4 ml/l	-	20-40 ml/l
Caustic soda flake	50 g/l	50 g/l	4-8 g/l
Nesto Scour LV4	5 g/l	5 g/l	1-2 g/l
Nascent - O2	-	-	6-8 g/l

Pad at 30°C and steam at 100°C for 20-30 mins. followed by washing (hot-warm-cold)

1.2 Combined Scour-Bleach

Nestogen JDP	2-4 g/l
Nascent - O2	6-8 g/l
Nesto Scour LV4	1-2 g/l
Caustic Soda flakes	10-20 g/l
Hydrogen Peroxide (50%)	40-60 ml/l

Pick up : 120-140%

Steam at 100°C for 10-20 mins followed by wash-off (95°C/95°C/80°C/50-70°C)

2. DISCONTINUOUS PROCESS (BATCH OPERATION)**2.1 Pad-Batch**

	Oxidative Desize	Scouring
Nestogen JDP	3-5 g/kg	3-5 g/l
Nesto Scour LV4	1-2 g/kg	3-5 g/l
Hydrogen Peroxide	12-17 ml/kg	-
Caustic Soda	8-10 g/kg	40-60 g/l

Pick up : 100%

Desize: Pad-batch at 90°C for 1 hour

Scouring : Pad at 50-90°C and batch at 90°C for 2-3 hours.

**Storage
Packing**

Stable under normal conditions.
50 Kg. Plastic Carboy

The product appearance varies from batch to batch. The colour & viscosity may vary from batch to batch and its intensity is not an indication of product strength.

NONWARRANTY: The suggestions and data in this bulletin are based on information we believe to be reliable. They are offered in good faith but without guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions on an experimental basis before adopting them on a commercial scale.