

TECHNICAL BULLETIN

Textile Processing Compound



Let You LEAD The Process

E-mail : contact@nestorindustries.com

Solvo Stain SR

Economic Stain Removing Agent for synthetic textile substrate

Solvo Stain SR is highly efficient stain removing & scouring agent for the pre-treatment of synthetic textile processing. It exhibits a range of desirable properties which give it multiple uses in synthetic textile pre-treatment processing.

Dynamic Properties are as under :

1. Excellent scouring agent
2. Effective stain remover
3. Very good swelling agent
4. Stable and very effective in acidic bath
5. Imparts excellent whiteness to the fabrics

Above all properties impart exclusive and extra-ordinary feel to the treated fabrics.

Characteristics:

Appearance	:	Transparent water white to pale straw coloured liquid
Ionic Nature	:	Non - ionic
Composition	:	Blend of organic surfactants & ester
Solubility	:	Miscible in all proportions in water
Stability to hard water	:	Very Good
pH	:	6.0 ± 0.5

Guide Recipe :

Solvo Stain SR	=	1 – 2% O. W. F.
Caustic Flakes	=	Quantity depends upon quality of fabrics
Soda Ash	=	Optional ***

Application Method:

Directly add **Solvo Stain SR** in the bath water and then load textile goods in HTHP jet machine with temperature gradient of 1 to 2°C.

Raise the temperature to 90°C and hold for 20 minutes.

Further raise temperature to 130°C and hold for 45-60 minutes.

It is recommended to give OXALIC wash along with 100 – 200 Gms of N. I. D. (9.5 mole) to the treated goods.

Storage Stable under normal conditions.
Packing 50 Kg. Plastic Carboy

The product appearance varies from batch to batch. The colour & viscosity may vary from batch to batch and its intensity is not an indication of product strength.

NONWARRANTY: The suggestions and data in this bulletin are based on information we believe to be reliable. They are offered in good faith but without guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions on an experimental basis before adopting them on a commercial scale.

Head Office Address: Plot No – 538, GIDC, Pandesara, Surat – 394221
Contact No. - +91 8306083020, +91 9377781836 || Website : www.nestorindustries.com